

TECHNICAL DATA SHEET

DOT-WM-07-S/13-S DOT-WG-07-S/13-S



PVC white matt & gloss

| ltem | Description | Specification |
|-----------------------------|---|---|
| Composition | Type of support | Monomeric PVC - 100 micron |
| | Available dimension | 1,07-1,37*50m |
| | Finish | White - matt coated / white - gloss coated |
| | Layers | Front Layer: PVC 100 my ± 5 (150 gsm ± 5) |
| | | Liner: stabilized monosilicone kraft paper 120 my |
| | | Back treatment: dot shaped pressure sensitive removable self- adhesive polyacrylate adhesive 20 my |
| | Total thickness & weight | 240 my ±5 (260 gsm ±5) |
| Technical data Application | Elongation at Break (ASTM D638 M89 - %) | >150% |
| | Release force | 0.1 ≤ x ≤ 0.15 N/25mm |
| | Peeling force (24h) | 2.0 ≤ x ≤ 5.0 N/25mm |
| | Dimensional Stability (MD)-(ASTM D1204-02) | ≤ 0.1 in |
| | Surface Tension (ASTM D2578-04°) | 32 ÷ 36 dyne/cm |
| | Fire resistance (DIN-4102-1) | B1 |
| | Working temperature (24h after application) | -20 ÷ 80 °C |
| | Application temperature | 8 ÷ 30 °C |
| | Sun exposure (European climate conditions): 3 - 4 months average exposure time. Installation recommendations: it is obviously very important that the surface on which you are going to apply the product must be appropriately clean and smooth and free of defects before application, as required for any kind of applications. We recommend applications of no more than 3 months, otherwise the adhesive can go permanent. | |
| Storage Period | 6 months under ordinary conditions at the mean temperature of 23 ± 2°C (min. 18°C, max. 25°C) and relative humidity of 40 - 65%. A high storage temperature and humidity may decrease the ink absorption. | |
| | - Suitable for screen printing and digital printing. | |
| Printing Compatibility | - Suitable for eco-solvent, UV Curable and Latex inks (Latex: tested on Mimaki JV400LX und HP series 300/3000 (when working with other machines, tests before printing are recommended) Note: best printing conditions: 16-28°C, humidity 30-60%. Notice: when realizing saturated images, the die cutting at the edges of the printed image has to be avoided; it would be better to leave an edge of a few millimeters from the printed area, to prevent the image edges from curling. Anyway, if you cut the printed areas, it is highly recommended that the ink drying process is completed, be aware that the ink is totally dryed or cured before cutting the selvedges. Notes: due to the wide number of ink producers and digital printing machines, weather conditions and printing variability tests before printing are recommended. | |
| REACH Regulation | Complying with the Italian Decree-Law nbr. 133 issued on 14.09.2009 and published on the Italian <i>Gazzetta Ufficiale</i> , we inform that the product complies with the REACH regulation with regard to the substances and chemicals. For further information, please refer to the certified copy available of the analyses worked out on the substances taken into consideration by REACH (Registration Evaluation Authorization of CHemicals). | |
| Notes | Published information is based upon research and information which the Company believes to be reliable although such information does not constitute a warranty. Because of the variety of uses of the products and the continuing development of new applications, the purchaser should carefully consider the suitability and performance of the product for each intended use, and the purchaser shall assume all risks regarding such use. The seller shall not be liable for damages in excess of the purchase price of the product nor for incidental or consequential damages. All specifications are subject to changes without prior notice. | |



