

JT 10800 WG-BFG

PRODUCT DESCRIPTION

Highly conformable self-adhesive cast PVC printing media. With its repositionable properties it allows the product to glide effortless across the surface until it is fixated in its final position.

Face Material: 50 µm white gloss, cast PVC

Adhesive: Solvent repositionable Bubble-free, dark grey

Liner: PE coated Bubble-free liner, 155 g/sqm

TYPICAL USE

Long-term applications for demanding corrugations such as full vehicle wrapping and highly conformable 3D surfaces.

The product is developed for vehicle markings on flat, curved, embossed or riveted surfaces.

PROCESSING

Especially designed for solvent based, eco-solvent, mild solvent and Latex inkjet printing on wideformat printing equipment.

UV printing is also possible as long as the selected inks are flexible enough for the expected deformation. If printed on UV, please adapt your print speed and curing settings.

To achieve optimal protection and durability, JT 10800 WG-BFG needs to be laminated with LF 10700 Series.

To achieve the best possible print quality, please make sure that the correct ICC profiles and printer settings are used. Profiles can be obtained from our subsidiaries or distributors, or can be downloaded from: www.mactacgraphics.eu. The ICC profiles are provided solely as a customer resource.

Print environments, the individual nature of printing systems, inks and software can significantly affect output. It is the customer's responsibility to determine the suitability of any profile for use in their specific print environment.

For further information on printing, application and removal, please refer to "TB 4.2 Application Bulletin of JT 10800 Series"

To ensure application suitability, always test the proposed construction under actual application and end-use conditions before going into full production.

SHELF LIFE

2 years when stored at 15 to 25°C and ± 50 % relative humidity (in the original packaging).

PHYSICAL PROPERTIES (TYPICAL VALUES)

Average Values Test Method

Thickness		
Film (microns)	50 µm	ISO:534
Adhesive data, 23°C (N/25 mm)		
Peel adhesion 180° on stainless steel		
- 20 min. residence	11.5	FTM1
- 24 hour residence	14.5	FTM1
Dimensional stability		
Shrinkage (48 hours at 70°C applied on Aluminium)	Max. 0.3mm	FTM14
Temperature ranges		
Minimum application temperature (°C)	≥15 °C	
Service temperature range (°C)	-20°C - +70°C	
Certifications		
Fire Classification		EN13501-1

EXPECTED DURABILITY

Central Europe Zone 1

Unprocessed	7 years	ISO 4892-2
Printed & laminated*	Up to 5 years	ISO 4892-2

DISCLAIMER

For more information on the durability and exposure please visit the "Mactac Technical Bulletin TB 7.5 Outdoor Durability of Mactac Graphics - Self-adhesive films" on the www.mactacgraphics.eu website.

Avery Dennison warrants that its Products meet its specifications. Avery Dennison gives no other express or implied guarantees or warranties with respect to the Products, including, but not limited to, any implied warranties of merchantability, fitness for any particular use and/or non infringement. All Avery Dennison products are sold with the understanding that the purchaser has independently determined the suitability of such products for its purposes. The period of warranty is one (1) year from the date of shipment unless expressly provided otherwise in the product data sheet. All Avery Dennison's products are sold subject to Avery Dennison's general terms and conditions of sale, see <http://terms.europe.averydennison.com>. Avery Dennison's aggregate liability to Purchaser, whether for negligence, breach of contract, misrepresentation or otherwise, shall in no circumstances exceed the price of the defective, non-conforming, damaged or undelivered Products which give rise to such liability as determined by net price invoices to Purchaser in respect of any occurrence or series of occurrences. In no circumstances shall Avery Dennison be liable to Purchaser for any indirect, incidental or consequential loss, damage or injury, including without limitation, loss of anticipated profits, goodwill, reputation, or losses or expenses resulting from third party claims.