

EASY PUFF PLUS

SPECIFICATIONS

Composition	Average Thickness	Carrier	Certifications
PU water based	210-230 microns	adhesive polyester	REACH compliant  

APPLICATION INSTRUCTIONS

APPLIES ON	SUGGESTED CUTTING SETTINGS			TRANSFER SETTINGS			
cotton, polyester, poly/cotton blends, elastic fabrics not treated with silicon or died with sublimation inks							
	Blade	Pressure	Speed	Time	Temperature	Pressure	Peel
	45°	70 gf	15 cm/sec	8 sec	125°C	low 1.5 bar	hot

- Cut mirrored and peel off excess material
- Just before the 1st transfer, preheat the lower platen for 20 sec
- Place the decoration on the fabric
- Apply following the recommended parameters with a heat press (not with a home iron)
- Remove the carrier while hot

PRODUCT HIGHLIGHTS

- Machine washable
- 3D-effect and soft and elastic
- Suitable for elastic fabrics

-  ! Even when using the recommended parameters, due to the different chemistry of each colour, the result may slightly vary.
! We recommend to perform a test before launching a production! (+/- 5°C).
! When using a manual heat press, lift the heat platen quickly for the best result (puff effect)

CARE AND WASHING RECOMMENDATIONS

Washing	Ironing	Tumble dry	Dry cleaning	Storage Shelf Life	Storage Temperature	Storage Conditions	Position
30°C inside out	Yes Program: silk inside out	NO	NO	Up to 2 years	Between 18°C and 26°C	Away from sunlight and dust	Vertical

- Wait 24 hours after the application before the first wash
- Respect the textile recommendations
- Do not bleach or use aggressive chemical agents

 This document can be subject to variations. Updated versions are available on www.siser.com
For further information, please contact our sales office: info@siser.it



Siser s.r.l.
Viale della Tecnica, 18
36100 Vicenza - Italy

Tel. +39 0444.287960
Fax +39 0444.287959
info@siser.it
www.siser.com

r.e.a. vi 171856
reg. imp. vi n° 14971
c.s. € 103.300 i.v.
p.iva 01591490246



Management
System
ISO 9001:2015
ISO 14001:2015
www.tuv.com
ID: 9105027958

