productinformation

tesa® 4952

1150 µm double sided PE foam tape

tesa® 4952 is a double sided PE foam tape for constructive mounting applications. It consists of a highly conformable PE foam backing and a tackified acrylic adhesive. tesa® 4952 has been externally certified for furniture mirror mounting.

Product benefits:

- Versatile adhesive for high immediate adhesion on numerous substrates
- Fully outdoor suitable: UV, water and ageing resistant
- Compensates for differing thermal expansion of dissimilar materials
- High immediate bonding strength even at low bonding pressure
- Very good cold shock absorbtion

Main Application

- Furniture mirror mounting
- Mounting of car mirrors
- Mounting functional trims & profiles
- Mounting of decorative panels

Technical Data

| • | Backing material | PE foam | • | Tensile strength | 10 N/cm |
|---|---------------------|-------------------|---|--------------------|-------------|
| • | Color | white | • | Type of liner | glassine |
| • | Total thickness | 1150 μm | • | Colour of liner | brown |
| • | Type of adhesive | tackified acrylic | • | Thickness of liner | 70 μm |
| | Elongation at break | 200 % | | Weight of liner | $80 g/m^2$ |

Adhesion to

| • | Steel (initial) | 6.5 N/cm | • | Steel (after 14 days) | 8.0 N/cm |
|---|---------------------|----------|---|---------------------------|----------|
| • | ABS (initial) | 5.0 N/cm | • | ABS (after 14 days) | 8.0 N/cm |
| • | Aluminium (initial) | 5.0 N/cm | • | Aluminium (after 14 days) | 8.0 N/cm |
| • | PC (initial) | 5.0 N/cm | • | PC (after 14 days) | 8.0 N/cm |
| • | PE (initial) | 2.7 N/cm | • | PE (after 14 days) | 2.8 N/cm |
| | PET (initial) | 5.0 N/cm | • | PET (after 14 days) | 7.0 N/cm |
| | PP (initial) | 2.8 N/cm | • | PP (after 14 days) | 5.5 N/cm |
| • | PS (initial) | 5.0 N/cm | • | PS (after 14 days) | 7.5 N/cm |
| • | PVC (initial) | 5.0 N/cm | • | PVC (after 14 days) | 8.0 N/cm |

For latest information on this product please visit http://l.tesa.com/?ip=04952

great to work with

tesa® 4952

1150 μm double sided PE foam tape

Properties

| • | lemperature resistance short term | |
|---|--|--|
| | The second section and design and the section is | |

Temperature resistance long term

Tack

Ageing resistance (UV)

Humidity resistance

80 °C

Resistance to chemicals

Softener resistance

Static shear resistance at 23°C

Static shear resistance at 40°C

•••

•••

Evaluation across relevant tesa® assortment: • • • • very good

a a a wor

very good ••• good

d

• • medium

low

Additional Information

tesa® 4952 has been tested and approved by LGA institute for mirror mounting. Report number IWQ FSG 329 1189.

Peel Adhesion:

- immediately: foam splitting on Steel, Aluminium, ABS, PC, PS, PET, PVC
- after 14 days: foam splitting on Steel, Aluminium, ABS, PC, PS, PET, PVC