

J53I30 | SLP Glossy 200

COATED PAPER WITH SLP

PRODUCT SPECIFICATION *

Weight DIN EN ISO 536	g/m ²	208	± 7
Thickness DIN EN ISO 534	µm	192	± 7
	mil	7.6	± 0.3
Gloss BYK (60°) ISO 2813		39	± 5
Colour Elrepho UVO (D65) ISO 2469	L	96,2	± 0,5
	a	0,2	± 0,3
	b	2,8	± 0,6
	delta b	12,6	± 0,8
CIE whiteness (D65/10°) min. ISO 2469		> 136	
Opacity min. ISO 2469	%	> 91	

Printability

Simplex printable

Laminatability

Hot & cold

Printing Technology

🟠 Inkjet solvent

🔵 Inkjet latex

🟣 Inkjet UV

Compatibility

Excellent results on all eco, mild and hard solvent printers as well as on latex and UV printers. Certified for HP Latex printers.

Certificates

Certified for
HP Latex Inks

Certified for HP Latex Inks

Directions for use

Store material only in original packaging under normal climatic conditions (23°C, 50 % RH). Protect material from direct sunlight. It is recommended to adapt the material to indoor climate at least 24 hours before usage.

* Modifications reserved.

Version 04/2017