


PolyZone Silver 20 Xtra

Film for Application to Rigid Plastic Glazing

OPTICAL & SOLAR PROPERTIES

| | Single Pane |
|----------------------------------|-------------|
| Visible Light Transmitted | 16 % |
| Visible Light Reflected (Int) | 63 % |
| Visible Light Reflected (Ext) | 64 % |
| Ultra Violet Block | 99 % |
| Total Solar Energy Reflected | 65 % |
| Total Solar Energy Transmitted | 12 % |
| Total Solar Energy Absorbed | 23 % |
| Emissivity (Room Side) | 0.84 |
| Glare Reduction | 82 % |
| Shading Coefficient | 0.22 |
| Solar Heat Gain Coeff. (G-Value) | 0.19 |
| U-Value Winter (IP) | 1.04 |
| U-Value Winter (SI) | 5.91 |
| Luminous Efficacy | 0.75 |
| Total Solar Energy Rejected | 81 % |

R0705XP - PolyZone Silver 20 Xtra Pressure Sensitive Adhesive



Ed-A DS No 1910 February 2013