

White Out Film

OPTICAL & SOLAR PROPERTIES

	Single Pane	Double Pane
Visible Light Transmitted	10 %	10 %
Visible Light Reflected (Int)		
Visible Light Reflected (Ext)	48 %	50 %
Ultra Violet Block	99 %	99 %
Total Solar Energy Reflected	36 %	34 %
Total Solar Energy Transmitted	17 %	15 %
Total Solar Energy Absorbed	47 %	51 %
Emissivity (Room Side)	0.90	0.90
Glare Reduction	89 %	89 %
Shading Coefficient	0.37	0.49
Solar Heat Gain Coeff. (G-Value)	0.31	0.42
U-Value Winter (IP)	1.07	0.49
U-Value Winter (SI)	6.08	2.78
Luminous Efficacy	0.27	0.19
Total Solar Energy Rejected	69 %	58 %

R073WO - White Out Pressure Sensitive Adhesive Film

ED-A DS No 1801 February 2013